

[transparent calendered]

Ideal for producing bags and coupling to various materials



ERMOGLASS

APPROVALS

1935/2004/CE
DM italian 21/03/73
BfR XXXVI
FDA 21 CFR § 176.170 and § 176.180

APPLICATIONS

Especially suggested for making envelopes and bag windows.
Suitable for waxing, printing and PE lamination.

DESCRIPTION

Calendered paper with high transparency, OBA free.
Substances: from 35 gsm.

PARAMETERS	Unit	Method	Typical Value	Tolerances
Substance	g/m ²	ISO 536	35	+/- 1,5
Tensile strength md	kN/m	ISO 1924-2	3,2	>= 2,6
Tensile strength cd	kN/m	ISO 1924-2	1,6	>= 1,3
Stretch md	%	ISO 1924-2	1,2	>= 0,9
Stretch cd	%	ISO 1924-2	7	>= 5,6
Transparency	%	ISO 22891	83	>= 80
Moisture content	%	ISO 287	6,5	+/- 1