

[grease resistant]

Ideal for paper bags for greasy and moist foods

ERMOPACK RU RG SCO



APPROVALS

1935/2004/CE
DM italian
BfR
FDA
Directive 94/62/CE

APPLICATIONS

Suitable for PE extrusion and
ALU lamination.

DESCRIPTION

Greaseproof treated on one side with
kit test 8, wet strength, OBA free.
PFOA and PFOS free.

PARAMETERS	Unit	Method	Typical Value		
Substance	g/m ²	ISO 536	40	50	60
Tensile strength md	kN/m	ISO 1924-2	3,4	4,2	5,6
Tensile strength cd	kN/m	ISO 1924-2	2	2,4	2,6
Wet tensile strength MD	kN/m	ISO 3781	0,65	0,8	0,95
Kit test	n°	ISO 16532-2	8		
Moisture content	%	ISO 287	5,5	5,5	5,5