

[for coupling]

Ideal for coupling to aluminium for food wrapping

## ERMOTENAX RL SCO/CCO



### APPROVALS

1935/2004/CE  
DM italian  
BfR  
FDA  
Directive 94/62/CE

### APPLICATIONS

Suggested for ALU lamination/PE extrusion.

### DESCRIPTION

MG paper, available with OBA or OBA free.

PARAMETERS	Unit	Method	Typical Value		
Substance	g/m <sup>2</sup>	ISO 536	30	40	50
Tensile strength md	kN/m	ISO 1924-2	1,9	2,4	3,1
Tensile strength cd	kN/m	ISO 1924-2	1,3	1,8	2,2
Smoothness Bekk (smooth. side)	s	ISO 5627	250	190	150
Moisture content	%	ISO 287	5	5	5