



KRAFT MP SCO/CCO



APPROVALS

1935/2004/CE
DM italian
BfR
FDA
Directive 94/62/CE

APPLICATIONS

Recommended for PE extrusion, lamination with aluminium or combined lamination also with plastic film.

DESCRIPTION

Calandered one side coated with OBA or OBA free, with excellent printability both with flexographic printing and rotogravure.

PARAMETERS	Unit	Method	Typical Value				
Substance	g/m ²	ISO 536	40	50	50	70	80
Tensile strength md	kN/m	ISO 1924-2	2,2	2,8	3,3	4,3	4,9
Tensile strength cd	kN/m	ISO 1924-2	1,2	1,5	1,8	2,5	2,8
Opacity	%	ISO 2471	71	76	81	83	85
Roughness PPS (smooth. side)	µm*100	ISO 8791-4	90	80	80	80	80
Moisture content	%	ISO 287	5,5	5,5	5,5	4,5	4,5