



PELLEAGLIO FP SCO/CCO



APPROVALS

1935/2004/CE
DM italian
BfR
FDA
Directive 94/62/CE

APPLICATIONS

Suitable for full printing for gift wrapping.

DESCRIPTION

Slightly pigmented calendered paper granting good printability also with full printing. Available in the versions OBA or OBA free.

PARAMETERS	Unit	Method	Typical Value			
Substance	g/m ²	ISO 536	40	50	55	60
Tensile strength md	kN/m	ISO 1924-2	2,8	3,1	3,5	4,1
Tensile strength cd	kN/m	ISO 1924-2	1,6	1,7	1,8	2,1
Opacity	%	ISO 2471	67	70	72	75
Roughness PPS (smooth. side)	µm*100	ISO 8791-4	110	110	110	110
Moisture content	%	ISO 287	5,5	5,5	5,5	5,5



PELLEAGLIO SCO/CCO



APPROVALS

1935/2004/CE
DM italian
BfR
FDA
Directive 94/62/CE

APPLICATIONS

Suitable for flexographic and rotogravure printing, ALU lamination and PE.

DESCRIPTION

Calendered grade with good opacity, available OBA or OBA free.

PARAMETERS	Unit	Method	Typical Value			
Substance	g/m ²	ISO 536	40	50	55	60
Tensile strength md	kN/m	ISO 1924-2	2,4	3,2	3,5	3,7
Tensile strength cd	kN/m	ISO 1924-2	1,5	1,7	1,9	1,8
Opacity	%	ISO 2471	64	68	70	72
Roughness PPS (smooth. side)	µm*100	ISO 8791-4	230	200	200	200
Moisture content	%	ISO 287	6	6	6	6