



PELURE E SAT PP



APPROVALS

1935/2004/CE
DM italian
BfR
FDA
Directive 94/62/CE

APPLICATIONS

Suitable for waxing, printing,
ALU and PE lamination, bags manufacturing
(and bag windows).

DESCRIPTION

Calendered transparent paper, OBA free.
Available wet strenght version too.

Parameters	Unit	Method	PELURE E SAT PP					PELURE E SAT PP RU		
			Typical Value							
Substance	g/m ²	ISO 536	25	30	35	40	45	32	35	40
Tensile strength md	kN/m	ISO 1924-2	2,3	2,7	3,2	3,7	4,1	3	3,3	3,7
Tensile strength cd	kN/m	ISO 1924-2	1,1	1,3	1,6	1,8	2	1,8	2	2,2
Wet tensile strength MD	kN/m	ISO 3781						0,55	0,6	0,65
Transparency	%		77	74	70	67	64	73	70	67
Moisture content	%	ISO 287	6	6	6,5	6,5	6,5	6,5	6,5	6,5