



[matt calendered]

## TWISTING MP SCO/CCO



### APPROVALS

1935/2004/CE  
DM italian  
BfR  
FDA  
Directive 94/62/CE

### APPLICATIONS

Suitable for wrapping of all kind of candies  
(with or without end twisting).

### DESCRIPTION

Twisting grade slightly coated on one side  
for better printability, available with OBA  
or OBA free.

PARAMETERS	Unit	Method	Typical Value	
Substance	g/m <sup>2</sup>	ISO 536	40	45
Tear (Elmendorf) md	kN/m	ISO 1924-2	160	200
Tear (Elmendorf) cd	kN/m	ISO 1924-2	170	220
Opacity	%	ISO 2471	67	72
Roughness PPS (smooth. side)	µm*100	ISO 8791-4	120	120
Moisture content	%	ISO 287	7	7



## TWISTING SCO/CCO



### APPROVALS

1935/2004/CE  
DM italian  
BfR  
FDA  
Directive 94/62/CE

### APPLICATIONS

Recommended for wrapping all kind of candies after waxing; capable to maintain twisting.

### DESCRIPTION

Calandered grade, available OBA or OBA free.  
High tear strength.

PARAMETERS	Unit	Method	Typical Value
Substance	g/m <sup>2</sup>	ISO 536	40
Tear (Elmendorf) md	kN/m	ISO 1924-2	200
Tear (Elmendorf) cd	kN/m	ISO 1924-2	230
Opacity	%	ISO 2471	65
Roughness PPS (smooth. side)	µm*100	ISO 8791-4	280
Moisture content	%	ISO 287	7