

[tissue for miscellaneous wrappings]

Ideal for general packaging used for wrapping objects

VELINA
SD RL CCO



APPROVALS

1935/2004/CE
DM italian
BfR
FDA
Directive 94/62/CE

APPLICATIONS

Suggested for diversified wrapping and PE extrusion.

DESCRIPTION

MG paper, only available with OBA.

PARAMETERS	Unit	Method	Typical Value			
Substance	g/m ²	ISO 536	20	25	30	40
Tensile strength md	kN/m	ISO 1924-2	0,95	1,2	1,5	2,2
Tensile strength cd	kN/m	ISO 1924-2	0,7	0,9	1,1	1,5
Smoothness Bekk (smooth. side)	s	ISO 5627	350	320	300	200
Moisture content	%	ISO 287	5	5	5	5