


[wet resistant]

Velina with WS treatment, suitable for creping

VELINA VP ML SCO/CCO



APPROVALS

1935/2004/CE
DM italian
BfR
FDA
Directive 94/62/CE

APPLICATIONS

Suitable for lamination with ALU and PE,
for chocolate or citrus wrapping.
WS version suggested for impregnation
and further creping.

DESCRIPTION

MG paper with good mechanical strength
available with OBA or OBA free also in wet
strength version.

PARAMETERS	Unit	Method	VELINA VP ML SCO/CCO		SCO/CCO RU	
			Typical Value			
Substance	g/m ²	ISO 536	20	22	19	22
Tensile strength md	kN/m	ISO 1924-2	1,2	1,3	1,1	1,3
Tensile strength cd	kN/m	ISO 1924-2	0,85	0,9	0,9	1
Wet tensile strength MD	kN/m	ISO 3781			0,25	0,28
Smoothness Bekk (smooth. side)	s	ISO 5627	315	350	350	350
Moisture content	%	ISO 287	4,5	4,5	4,5	4,5