

[for coupling]

Ideal for coupling to aluminium for food wrapping

VELINA VP RL CER SCO



APPROVALS

1935/2004/CE
DM italian
BfR
FDA
Directive 94/62/CE

APPLICATIONS

Suitable for lamination with ALU after waxing and for embossing. Good printability.

DESCRIPTION

MG paper with good mechanical strength, highly refined, excellent sheet formation, OBA free.

PARAMETERS	Unit	Method	Typical Value		
Substance	g/m ²	ISO 536	20	22	25
Tensile strength md	kN/m	ISO 1924-2	1,2	1,3	1,6
Tensile strength cd	kN/m	ISO 1924-2	1	1,1	1,2
Smoothness Bekk (smooth. side)	s	ISO 5627	450	450	360
Moisture content	%	ISO 287	4,5	4,5	4,5